

Application No.: 10/806556
Docket No.: EL0508USNA

Page 2

Amendments to the Specification

At page 11, lines 25 – 27 replace the current paragraph with the following:

-- The substrate is typically a rigid substrate such as glass. The firing process may optionally include a rapid cool-down stage for the manufacture of toughened glass. --